

skheme®

brembana

brembana

marble

technical data

properties	value
DENSITY	2705 kg/mc
COMPRESSIVE STRENGTH	122 MPa
FLEXURAL STRENGTH	6.5 MPa
OPEN POROSITY	0.57%
WATER ABSORPTION	0.2%
FROST RESISTANCE	Partly

Variation is an inherent property of tiles and stone.



The information provided in this Technical Data Sheet is given in good faith and reflects current knowledge and experience. It is intended as a general guide and may be updated without notice. Users are responsible for ensuring the product's suitability for their specific application and for compliance with all relevant local building codes, Australian Standards, and regulations. This information is offered for guidance purposes only and does not constitute any representation or warranty, express or implied. Any applicable warranties are governed solely by the terms and conditions of sale and relevant statutory requirements under Australian Consumer Law.