

skheme®

---

carrara plus

---

# carrara plus

marble

## technical data

| properties           | value      |
|----------------------|------------|
| DENSITY              | 2699 kg/mc |
| COMPRESSIVE STRENGTH | 131 MPa    |
| FLEXURAL STRENGTH    | 5.5        |
| OPEN POROSITY        | 0.7%       |
| WATER ABSORPTION     | 0.2%       |
| FROST RESISTANCE     | Partly     |

Variation is an inherent property of tiles and stone.

