



skheme®

crema antico

crema antico

marble

technical data

properties	value
DENSITY	2670 kg/mc
COMPRESSIVE STRENGTH	63 MPa
BENDING STRENGTH	11.6 MPa
WATER ABSORPTION	0.15%

Variation is an inherent property of tiles and stone.

