

flute



technical information

carrara

properties	value
DENSITY	2699 kg/mc
COMPRESSIVE STRENGTH	130 MPa
FLEXURAL STRENGTH	22 MPa
OPEN POROSITY	0.7%
WATER ABSORPTION	0.2%
FROST RESISTANCE	Partly
IMPORTANT	FLUTE is a decorative design element for vertical surfaces only and should be handled with care. The product should be supported on both ends, preferably carried vertically when once removed from the box. Installation should be completed on a non-moisture sensitive substrate, using a fast setting adhesive, stone friendly grout and silicones. Upon installation, the stone should be sealed with appropriate stone sealer, prior and after grouting.

Variation is an inherent property of tiles and stone. Sizes are nominal and may include a joint.

flute



technical information

lloret

properties	value
DENSITY	2770 kg/mc
COMPRESSIVE STRENGTH	161 MPa
FLEXURAL STRENGTH	7.5 MPa
WATER ABSORPTION	1%
FROST RESISTANCE	Partly
IMPORTANT	FLUTE is a decorative design element for vertical surfaces only and should be handled with care. The product should be supported on both ends, preferably carried vertically when once removed from the box. Installation should be completed on a non-moisture sensitive substrate, using a fast setting adhesive, stone friendly grout and silicones. Upon installation, the stone should be sealed with appropriate stone sealer, prior and after grouting.

Variation is an inherent property of tiles and stone. Sizes are nominal and may include a joint.

flute



technical information

epoca

properties	value
DENSITY	2871 kg/mc
COMPRESSIVE STRENGTH	237 MPa
FLEXURAL STRENGTH	15.75 MPa
OPEN POROSITY	0.62%
WATER ABSORPTION	0.24%
IMPORTANT	FLUTE is a decorative design element for vertical surfaces only and should be handled with care. The product should be supported on both ends, preferably carried vertically when once removed from the box. Installation should be completed on a non-moisture sensitive substrate, using a fast setting adhesive, stone friendly grout and silicones. Upon installation, the stone should be sealed with appropriate stone sealer, prior and after grouting.

Variation is an inherent property of tiles and stone. Sizes are nominal and may include a joint.