

skheme®

taj mahal super

taj mahal super

quartzite

technical data

properties	value
DENSITY	2,500/2650 kg/m³
FLEXURAL STRENGTH	16.5 MPa
WATER ABSORPTION	0.15%
ABRASION RESISTANCE	17.5 mm
IMPACT RESISTANCE	45 cm

Variation is an inherent property of tiles and stone.

