

skheme®

travertino navona unfilled

travertino navona unfilled

travertine

technical data

properties	value
COMPRESSIVE TENSILE STRENGTH	957 kg/ cm ²
UNIT BENDING TENSILE STRENGTH	127 kg/cm ²
COEFFICIENT OF LINEAR THERMAL EXPANSION	0,0045 mm/m°C
WATER IMBIBITION COEFFICIENT	1.00 %
IMPACT RESISTANCE, MINIMUM DROP HEIGHT	29 cm
WEIGHT PER UNIT VOLUME	2410 kg/m ³

Variation is an inherent property of tiles and stone.

