

T2



The T2 Terrazzo look without the associated maintenance. These porcelain tiles are available with six contemporary colours. T2 is suitable for all environments through the matt and grip finishes.

PRODUCT TYPE: Glazed Porcelain

COLOURS: Shale, Steel, Flint, Shadow, Vintage and

Parchment

SIZES: 300x600mm and 600x600mm

Rectified edges

FINISHES/USAGE: Matt and Grip / Floor and wall

AESTHETIC QUALITIES: Terrazzo look

TECHINICAL INFO: P3 Pendulum Slip Rating (Matt)

P5 Pendulum Slip Rating (Grip) P4 AWT (After 500 cycles) (Grip) More technical info on the last page

VARIATION:





PRODUCT SPECIFICATIONS

SIZES	FINISHES	SLIP RATING	TILE EDGE
300x600mm	MATT	P3 PENDULUM	RECTIFIED
600X600mm	MATT	P3 PENDULUM	RECTIFIED
300x600mm	GRIP*	P5 PENDULUM	RECTIFIED
600x600mm	GRIP*	P5 PENDULUM	RECTIFIED

^{*}The GRIP finish in all colours receives a Sustainable Slip Resistance value of P4 pendulum after 500 cycles

FORMATS

300x600mm









STEEL MATT



SHALE GRIP



STEEL GRIP



T2

PRODUCT SPECIFICATIONS

SIZES	FINISHES	SLIP RATING	TILE EDGE
300x600mm	MATT	P3 PENDULUM	RECTIFIED
600X600mm	MATT	P3 PENDULUM	RECTIFIED
300x600mm	GRIP*	P5 PENDULUM	RECTIFIED
600x600mm	GRIP*	P5 PENDULUM	RECTIFIED

^{*}The GRIP finish in all colours receives a Sustainable Slip Resistance value of P4 pendulum after 500 cycles

FORMATS

300x600mm






FLINT MATT



SHADOW MATT



FLINT GRIP



SHADOW GRIP




PRODUCT SPECIFICATIONS

SIZES	FINISHES	SLIP RATING	TILE EDGE
200 (00		DO DENIBULINA	DECTIFIED
300x600mm	MATT	P3 PENDULUM	RECTIFIED
600X600mm	MATT	P3 PENDULUM	RECTIFIED
300x600mm	GRIP*	P5 PENDULUM	RECTIFIED
600x600mm	GRIP*	P5 PENDULUM	RECTIFIED

^{*}The GRIP finish in all colours receives a Sustainable Slip Resistance value of P4 pendulum after 500 cycles (no grip finish available in Vintage)

FORMATS





PARCHEMENT MATT



VINTAGE MATT



PARCHMENT GRIP



T2







Variation is an inherent property of tiles and stone. Sizes are nominal and may include a joint.







TECHNICAL DATA

	technical characteristics Group B I a	test method	required values	value
888	water absorption	iso 10545-3	≤ 0.5%	0.21%
<u>6</u>	bending strength	iso 10545-4	≥12MPA	≥33.5MPA
60	breaking strength (S)	iso 10545-4	≥ 350 N	≥ 1785N
Ø	abrasion resistace	iso 10545-7	Max. 175 mm³ PEI 1-5	Class 3
	chemical resistance	iso 10545-13	Household chemicals and swimming pool salts	GA
•			Low concentration of acids and alkalis	GLA
2	stain resistance	iso 10545-14	Minimum Class 3	Class 5