




kan





Please note that all products must be fabricated using score & snap method and/or wet cutting in conjunction with AS/NZS 1716:2012, AS/NZS 1715:2009, AS/NZS 60335.2.69:2017. For more information please refer to: https://www.safework.nsw.gov.au

Variation is an inherent property of tiles and stone. Sizes are nominal and may include a joint.

left pictured: white right pictured: mustard











technical data

PROPERTIES	TEST METHOD	PRESCRIBED VALUES	RESULT
water absorption	ISO 10545-3	<0.5%	0.26%
modulus of rupture	ISO 10545-4	minimum 35	51.1
surface quality	ISO 10545-2	complies	100%
breaking strength	ISO 10545-4	≥ 1300 N	4361
resistance to staining	ISO 10545-14	declared value	class 5
resistance to chemicals	ISO 10545-13	minimum class B	A
scratch hardness	EN 15771	-	>6





Please note that all products must be fabricated using score & snap method and/or wet cutting in conjunction with AS/NZS 1716:2012, AS/NZS 1715:2009, AS/NZS 60335.2.69:2017. For more information please refer to: https://www.safework.nsw.gov.au

Variation is an inherent property of tiles and stone. Sizes are nominal and may include a joint.