

Colours shown in images may differ due to variations in photographic conditions and screen displays. Samples provided may not accurately reflect the exact shade or batch supplied, as variation is an inherent property of tiles and stone.






left pictured: diamond finish right pictured: dark grey entire formats

technical data

PROPERTIES	TEST METHOD	PRESCRIBED VALUES	VALUE
water absorption	ISO 10545-3	≤0.5%	0.21%
bending strength	ISO 10545-4	≥ 12 MPA	≥ 33.5MPA
breaking strength	ISO 10545-4	≥ 350 N	≥ 1785N
abrasion resistance	ISO 10545-7	Max. 175 mm³ PEI 1-5	class 3
resistance to chemicals	ISO 10545-13	Household chemicals & swimming pool salts	GA
		Low concentration of acids & alkalis	GLA
resistance to staining	ISO 10545-14	Minimum class 3	class 5



Please note that all products must be fabricated using score & snap method and/or wet cutting in conjunction with AS/NZS 1715:2009, AS/NZS 60335.2.69:2017. For more information please refer to: https://www.safework.nsw.gov.au