

skheme®

valais



# valais



alpine



savona



obsidian



604x1208mm



fire resistant



V3 variation

PRODUCT SPECIFICATIONS		format	size	finish	thickness	slip rating	colour
		tile	604x1208mm	natural	10mm	N/A	all colours
MATERIAL		glazed porcelain					
VARIATION		V3					
TILE EDGE		rectified					

Colours shown in images may differ due to variations in photographic conditions and screen displays. Samples provided may not accurately reflect the exact shade or batch supplied, as variation is an inherent property of tiles and stone.

Listed sizes and thicknesses are nominal and may vary slightly from actual working dimensions.

A 2/12-14 Neild Avenue Rushcutters Bay NSW 2010 | P 02 8755 2300 | W [www.skheme.com](http://www.skheme.com) | E [info@skheme.com](mailto:info@skheme.com)

left pictured: obsidian  
right pictured: alpine



# technical data

PROPERTIES	TEST METHOD	PRESCRIBED VALUES	VALUE
water absorption	ISO 10545-3	≤0.5%	≤0.06%
bending strength	ISO 10545-4	≥ 12 MPA	≥ 33.5MPA
breaking strength	ISO 10545-4	≥ 350 N	1780 N
abrasion resistance	ISO 10545-7	Max. 175 mm <sup>3</sup> PEI 1-5	class 3
resistance to chemicals	ISO 10545-13	Household chemicals & swimming pool salts	GA
		Low concentration of acids & alkalis	GLA
resistance to staining	ISO 10545-14	Minimum class 3	class 5



Please note that all products must be fabricated using score & snap method and/or wet cutting in conjunction with AS/NZS 1716:2012, AS/NZS 1715:2009, AS/NZS 60335.2.69:2017. For more information please refer to: <https://www.safework.nsw.gov.au>