

Kekule



PRODUCT TYPE: Natural stone

COLOURS: Blanc, Carrara, St Moritz Light, St Moritz Dark, Vert and Noir


SIZES: 100x300mm
Rectified edges

FINISHES/USAGE: Soapstone/Floor and Wall

AESTHETIC QUALITIES: An organic geometric feel, with the unique characteristics of real marble

TECHINICAL INFO: See last page for technical data

VARIATION:



V4


A Skheme creation, KEKULE is an evolution of the hexagon. The soapstone finish and natural stone qualities gives KEKULE the flexibility to be used for both wall and floor applications.

Kekule

PRODUCT SPECIFICATIONS

SIZES	FINISHES	TILE EDGE
100X300mm	SOAPSTONE	NON-RECTIFIED

FORMATS



100x300mm



BLANC SOAPSTONE




CARRARA SOAPSTONE



ST MORITZ LIGHT SOAPSTONE



ST MORITZ DARK SOAPSTONE



VERT SOAPSTONE



NOIR SOAPSTONE

Kekule



Kekule



Kekule

KEKULE VERT

technical characteristics	test method	result
water absorption	C97/C97M-09	0.26%
compressive strength (MPA)	C170/C170M-09	77 MPA
flexural strength (MPA)	C880/C880-09	25.2 MPA

KEKULE BLANC

technical characteristics	test method	result
water absorption	C97/C97M-09	0.24%
compressive strength (MPA)	C170/C170M-09	90 MPA
flexural strength (MPA)	C880/C880-09	12.5 MPA

KEKULE CARRARA

technical characteristics	test method	result
water absorption	C97/C97M-09	0.35%
compressive strength (MPA)	C170/C170M-09	138.9 MPA
flexural strength (MPA)	C880/C880-09	16.2 MPA

KEKULE NOIR

technical characteristics	test method	result
water absorption	C97/C97M-09	0.14%
compressive strength (MPA)	C170/C170M-09	205.4 MPA
flexural strength (MPA)	C880/C880-09	14.8 MPA

KEKULE ST MORITZ LIGHT AND DARK

technical characteristics	test method	result
water absorption	C97/C97M-09	4.40%
compressive strength (MPA)	C170/C170M-09	97 MPA
flexural strength (MPA)	C880/C880-09	14.5 MPA